

Test Report

(EVERLIGHT ELECTRONICS CO., LTD.)
 6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

(The following sample(s) was/were submitted and identified by the applicant as)

| | |
|--------------------------------------|--|
| BASIC INFORMATION | |
| Type of Product | DISPLAY |
| Supplier Company Name | EVERLIGHT |
| Address | NO.6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN |
| Tel / Fax / Email | TEL:886-2685-6688 |
| | FAX:886-2685-6699 |
| | E-MAIL: lindawang@everlight.com |
| Contact Person | LI LING WANG |
| EVERLIGHT REPORT NO | DISPLAY SERIES(Lead Frame Type Display) , Sampling Product : TDSL1160-SGS-14-Jun-2024 |
| PRODUCT INFORMATION | |
| Product/component Sample description | · Instrument panels · Digital readout displays |
| Quantity (numbers or weight) | 0.6975 g |
| EVERLIGHT P/N | DISPLAY SERIES(Lead Frame Type Display) , Sampling Product : TDSL1160 |
| Product Lot No | K2415L7-1 |
| Country of Origin | China |
| TEST INFORMATION | |
| Sample preparation | CUTTING |
| Test Method | RoHS: IEC 62321, Halogen: BS EN 14582 |
| MDL | Cd, Pb, Hg: 2 mg/kg, PBBs/PBDEs: 5 mg/kg, Halogen: 50 mg/kg |

(Sample Submitted By) : (EVERLIGHT ELECTRONICS CO., LTD.)

(Sample Receiving Date) : 31-May-2024
 (Testing Period) : 31-May-2024 to 14-Jun-2024

(Test Results) : (Please refer to following pages).



PIN CODE: AB214755

Test Report

(EVERLIGHT ELECTRONICS CO., LTD.)
 6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

- (Test Requested) : (1) RoHS 2011/65/EU Annex II (EU) 2015/863
 , DBP, BBP, DEHP, DIBP (As specified
 by client, with reference to RoHS 2011/65/EU Annex II and amending Directive
 (EU) 2015/863 to determine Cadmium, Lead, Mercury, Cr(VI), PBBs, PBDEs, DBP,
 BBP, DEHP, DIBP contents in the submitted sample(s).)
- (2) PAHs (As specified by client, to test PAHs and
 other item(s).)
- (Conclusion) : (1) , DBP, BBP,
 DEHP, DIBP RoHS 2011/65/EU Annex II (EU) 2015/863
 (Based on the performed tests on submitted sample(s), the test
 results of Cadmium, Lead, Mercury, Cr(VI), PBBs, PBDEs, DBP, BBP, DEHP, DIBP
 comply with the limits as set by RoHS Directive (EU) 2015/863 amending Annex II
 to Directive 2011/65/EU.)
- (2) (AfPS) GS
 PAHs 3 (Based upon the performed tests on the
 submitted sample(s), the test results of PAHs (15 items) comply with the limits of
 PAHs requirement (Category 3) Other consumer products as set by German
 Committee on Product Safety (AfPS) GS PAHs.)

(Test Part Description)

- No.1 : (BODY)
 No.2 : (PLATING LAYER OF SILVER COLORED METAL PIN)
 No.3 : (BASE MATERIAL OF SILVER COLORED METAL PIN)
 No.4 : () (SILVER COLORED METAL PIN (INCLUDING THE PLATING LAYER))

(Test Results)

| (Test Items) | (Method) | (Unit) | MDL | (Result) | | | (Limit) |
|---------------------|---|--------|-----|----------|------|------|---------|
| | | | | No.1 | No.2 | No.3 | |
| (Cd) (Cadmium (Cd)) | IEC 62321-5: 2013 | mg/kg | 2 | n.d. | --- | --- | 100 |
| (Pb) (Lead (Pb)) | (With reference to IEC 62321-5: 2013, analysis was performed by ICP-OES.) | mg/kg | 2 | n.d. | --- | --- | 1000 |

Test Report

(EVERLIGHT ELECTRONICS CO., LTD.)

6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

| (Test Items) | (Method) | (Unit) | MDL | (Result) | | | (Limit) |
|---|---|--------|------|----------|------|------|---------|
| | | | | No.1 | No.2 | No.3 | |
| (BBP) (Butyl benzyl phthalate (BBP)) | IEC 62321-8: 2017 / (With reference to IEC 62321-8: 2017, analysis was performed by GC/MS.) | mg/kg | 50 | n.d. | --- | --- | 1000 |
| (DBP) (Dibutyl phthalate (DBP)) | | mg/kg | 50 | n.d. | --- | --- | 1000 |
| (2-) (DEHP) (Di-(2-ethylhexyl) phthalate (DEHP)) | | mg/kg | 50 | n.d. | --- | --- | 1000 |
| (DIBP) (Diisobutyl phthalate (DIBP)) | | mg/kg | 50 | n.d. | --- | --- | 1000 |
| (DIDP) (Diisodecyl phthalate (DIDP)) (CAS No.: 26761-40-0, 68515-49-1) | | mg/kg | 50 | n.d. | --- | --- | - |
| (DINP) (Diisononyl phthalate (DINP)) (CAS No.: 28553-12-0, 68515-48-0) | | mg/kg | 50 | n.d. | --- | --- | - |
| (DNOP) (Di-n-octyl phthalate (DNOP)) (CAS No.: 117-84-0) | | mg/kg | 50 | n.d. | --- | --- | - |
| (DNPP) (Di-n-pentyl phthalate (DNPP)) (CAS No.: 131-18-0) | | mg/kg | 50 | n.d. | --- | --- | - |
| (DNHP) (Di-n-hexyl phthalate (DNHP)) (CAS No.: 84-75-3) | | mg/kg | 50 | n.d. | --- | --- | - |
| (2-) (DMEP) (Bis(2-methoxyethyl) phthalate (DMEP)) (CAS No.: 117-82-8) | | mg/kg | 50 | n.d. | --- | --- | - |
| (DMP) (Dimethyl phthalate (DMP)) (CAS No.: 131-11-3) | mg/kg | 50 | n.d. | --- | --- | - | |
| (DIOP) (Diisooctyl phthalate (DIOP)) (CAS No.: 27554-26-3) | mg/kg | 50 | n.d. | --- | --- | - | |

Test Report

(EVERLIGHT ELECTRONICS CO., LTD.)

6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

| (Test Items) | (Method) | (Unit) | MDL | (Result) | | | (Limit) |
|---|--|--------|------|----------|------|------|---------|
| | | | | No.1 | No.2 | No.3 | |
| (DNNP) (Di-n-nonyl phthalate (DNNP)) (CAS No.: 84-76-4) | IEC 62321-8: 2017 / (With reference to IEC 62321-8: 2017, analysis was performed by GC/MS.) | mg/kg | 50 | n.d. | --- | --- | - |
| (HBCDD) (- HBCDD, - HBCDD, - HBCDD) (Hexabromocyclododecane (HBCDD) and all major diastereoisomers identified (- HBCDD, - HBCDD, - HBCDD)) (CAS No.: 25637-99-4, 3194-55-6 (134237-51-7, 134237-50-6, 134237-52-8)) | IEC 62321: 2008 / (With reference to IEC 62321: 2008, analysis was performed by GC/MS.) | mg/kg | 5 | n.d. | --- | --- | - |
| (F) (Fluorine (F)) (CAS No.: 14762-94-8) | BS EN 14582: 2016 (With reference to BS EN 14582: 2016, analysis was performed by IC.) | mg/kg | 50 | 622 | --- | --- | - |
| (Cl) (Chlorine (Cl)) (CAS No.: 22537-15-1) | | mg/kg | 50 | 111 | --- | --- | - |
| (Br) (Bromine (Br)) (CAS No.: 10097-32-2) | | mg/kg | 50 | 4240 | --- | --- | - |
| (I) (Iodine (I)) (CAS No.: 14362-44-8) | | mg/kg | 50 | n.d. | --- | --- | - |
| (PFOS and its salts) (CAS No.: 1763-23-1 and its salts) | CEN/TS 15968: 2010 (With reference to CEN/TS 15968: 2010, analysis was performed by LC/MS/MS.) | mg/kg | 0.01 | n.d. | --- | --- | - |
| (PFOA and its salts) (CAS No.: 335-67-1 and its salts) | CEN/TS 15968: 2010 (With reference to CEN/TS 15968: 2010, analysis was performed by LC/MS/MS.) | mg/kg | 0.01 | n.d. | --- | --- | - |

Test Report

(EVERLIGHT ELECTRONICS CO., LTD.)

6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

| (Test Items) | (Method) | (Unit) | MDL | (Result) | | | (Limit) |
|--|---|--------|-----|----------|------|------|---------|
| | | | | No.1 | No.2 | No.3 | |
| (Polycyclic Aromatic Hydrocarbons) (PAHs) | | | | | | | |
| (a) (Benzo[a]pyrene) (CAS No.: 50-32-8) | AfPS GS 2019:01 PAK / (With reference to AfPS GS 2019:01 PAK, analysis was performed by GC/MS.) | mg/kg | 0.2 | n.d. | --- | --- | |
| (e) (Benzo[e]pyrene) (CAS No.: 192-97-2) | | mg/kg | 0.2 | n.d. | --- | --- | |
| (Benzo[a]anthracene) (CAS No.: 56-55-3) | | mg/kg | 0.2 | n.d. | --- | --- | |
| (b) (Benzo[b]fluoranthene) (CAS No.: 205-99-2) | | mg/kg | 0.2 | n.d. | --- | --- | |
| (j) (Benzo[j]fluoranthene) (CAS No.: 205-82-3) | | mg/kg | 0.2 | n.d. | --- | --- | |
| (k) (Benzo[k]fluoranthene) (CAS No.: 207-08-9) | | mg/kg | 0.2 | n.d. | --- | --- | |
| (Chrysene) (CAS No.: 218-01-9) | | mg/kg | 0.2 | n.d. | --- | --- | |
| (Dibenzo[a,h]anthracene) (CAS No.: 53-70-3) | | mg/kg | 0.2 | n.d. | --- | --- | |
| (Benzo[g,h,i]perylene) (CAS No.: 191-24-2) | | mg/kg | 0.2 | n.d. | --- | --- | |
| (Indeno[1,2,3-c,d]pyrene) (CAS No.: 193-39-5) | | mg/kg | 0.2 | n.d. | --- | --- | |
| (Anthracene) (CAS No.: 120-12-7) | | mg/kg | 0.2 | n.d. | --- | --- | |
| (Fluoranthene) (CAS No.: 206-44-0) | | mg/kg | 0.2 | n.d. | --- | --- | |
| (Phenanthrene) (CAS No.: 85-01-8) | | mg/kg | 0.2 | n.d. | --- | --- | |
| (Pyrene) (CAS No.: 129-00-0) | | mg/kg | 0.2 | n.d. | --- | --- | |
| (Naphthalene) (CAS No.: 91-20-3) | | mg/kg | 0.2 | n.d. | --- | --- | |
| 15 (Sum of 15 PAHs) | | mg/kg | - | n.d. | --- | --- | |

Test Report

(EVERLIGHT ELECTRONICS CO., LTD.)
6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

| (Test Items) | (Method) | (Unit) | MDL | (Result) | | | (Limit) |
|--|--|--------|-----|----------|------|------|---------|
| | | | | No.1 | No.2 | No.3 | |
| (Be) (Beryllium (Be)) (CAS No.: 7440-41-7) | US EPA 3052: 1996 (With reference to US EPA 3052: 1996, analysis was performed by ICP-OES.) | mg/kg | 2 | n.d. | --- | --- | - |
| (Cd) (Cadmium (Cd)) | IEC 62321-5: 2013 (IEC 62321-5: 2013 application of modified digestion by surface etching, analysis was performed by ICP-OES.) | mg/kg | 2 | --- | n.d. | --- | 100 |
| (Pb) (Lead (Pb)) | (IEC 62321-5: 2013 application of modified digestion by surface etching, analysis was performed by ICP-OES.) | mg/kg | 2 | --- | n.d. | --- | 1000 |
| (Hg) (Mercury (Hg)) | IEC 62321-4: 2013+ AMD1: 2017 (IEC 62321-4: 2013+AMD1: 2017 application of modified digestion by surface etching, analysis was performed by ICP-OES.) | mg/kg | 2 | --- | n.d. | --- | 1000 |
| (Cd) (Cadmium (Cd)) | IEC 62321-5: 2013 (With reference to IEC 62321-5: 2013, analysis was performed by ICP-OES.) | mg/kg | 2 | --- | --- | n.d. | 100 |
| (Pb) (Lead (Pb)) | (With reference to IEC 62321-5: 2013, analysis was performed by ICP-OES.) | mg/kg | 2 | --- | --- | 12.5 | 1000 |
| (Hg) (Mercury (Hg)) | IEC 62321-4: 2013+ AMD1: 2017 (With reference to IEC 62321-4: 2013+ AMD1: 2017, analysis was performed by ICP-OES.) | mg/kg | 2 | --- | --- | n.d. | 1000 |

Test Report

(EVERLIGHT ELECTRONICS CO., LTD.)
 6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

| (Test Items) | (Method) | (Unit) | MDL | (Result) | | | (Limit) |
|--|---|--------------------|-----|--------------------|------|------|---------|
| | | | | No.1 | No.2 | No.3 | |
| (Hexavalent Chromium) Cr(VI) (#2) | IEC 62321-7-1: 2015 (With reference to IEC 62321-7-1: 2015, analysis was performed by UV-VIS.) | µg/cm ² | 0.1 | --- | n.d. | n.d. | - |
| (Test Items) | (Method) | (Unit) | MDL | G (Result) (Limit) | | | |
| (Be) (Beryllium (Be)) (CAS No.: 7440-41-7) | US EPA 3050B: 1996 (With reference to US EPA 3050B: 1996, analysis was performed by ICP-OES.) | mg/kg | 2 | No.4 n.d. | - | | |

(Note)

1. mg/kg = ppm 0.1wt% = 0.1% = 1000ppm
2. MDL = Method Detection Limit ()
3. n.d. = Not Detected (); MDL / Less than MDL
4. "-" = Not Regulated ()
5. "---" = Not Conducted ()
6. (#2) =
 - a. 0.13 µg/cm² . / The sample is positive for Cr(VI) if the Cr(VI) concentration is greater than 0.13 µg/cm². The sample coating is considered to contain Cr(VI).
 - b. n.d. (0.10 µg/cm²) . / The sample is negative for Cr(VI) if Cr(VI) is n.d. (concentration less than 0.10 µg/cm²). The coating is considered a non-Cr(VI) based coating
 - c. 0.10 - 0.13 µg/cm² . / The result between 0.10 µg/cm² and 0.13 µg/cm² is considered to be inconclusive - unavoidable coating variations may influence the determination.
7. ILAC-G 8:09/2019 (w=0)
 (Unless otherwise stated, the decision rule for conformity reporting is based on Binary Statement for Simple Acceptance Rule (w=0) stated in ILAC-G8:09/2019. According to this rule, the judgement of conformity is based on the comparing test results with limits.)



Test Report

(EVERLIGHT ELECTRONICS CO., LTD.)
 6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

PFAS Remark

PFAS

PFAS

PFAS

PFAS

(PFAS)

PFAS)

(The quantitative technology of PFAS is to analyze the specific structure of PFAS substances. However, PFAS acid and its salts with the same carbon number group have the same specific structure that can be identified. The tested results of the analyzed specific structure cannot be distinguished to identify the contribution from PFAS acid or its salts. Therefore, the tested results display the sum of concentrations of PFAS acids and its salts with the same carbon number group. The concentration of PFAS substances in the below table have been included in the tested results, please refer to the table for relevant information: (The listed PFAS substances are examples only, it do not include all PFAS salts with the same carbon number group.))

| (Group Name) | (Substance Name) | CAS No. |
|--|--|-------------|
| PFOS, & (PFOS, its salts & derivatives) | (Perfluorooctane sulfonates) (PFOS) | 1763-23-1 |
| | (PFOS-K) Potassium perfluorooctanesulfonate (PFOS-K) | 2795-39-3 |
| | (PFOS-Li) Perfluorooctanesulfonic acid, lithium salt (PFOS-Li) | 29457-72-5 |
| | (PFOS-NH ₄) Perfluorooctanesulfonic acid, ammonium salt (PFOS-NH ₄) | 29081-56-9 |
| | (PFOS-NH(OH) ₂) Perfluorooctane sulfonate diethanolamine salt (PFOS-NH(OH) ₂) | 70225-14-8 |
| | (PFOS-N(C ₂ H ₅) ₄) Perfluorooctanesulfonic acid, tetraethylammonium salt (PFOS-N(C ₂ H ₅) ₄) | 56773-42-3 |
| | (PFOS-DDA) N-decyl-N,N-dimethyldecyl-1-aminium 1,1,2,2,3,3,4,4,5,5,6,6,7,7,8,8,8- heptadecafluorooctane-1-sulfonate (PFOS-DDA) | 251099-16-8 |

Test Report

(EVERLIGHT ELECTRONICS CO., LTD.)

6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

| (Group Name) | (Substance Name) | CAS No. |
|--|---|-------------|
| PFOS, & (PFOS, its salts & derivatives) | (PFOS-N(C ₄ H ₉) ₄) TetrabutylAmmonium perfluorooctanesulfonate (PFOS-N(C ₄ H ₉) ₄) | 111873-33-7 |
| | (POSF) Perfluorooctane sulfonyl fluoride (POSF) | 307-35-7 |
| | (PFOS-Mg) Perfluorooctanesulfonic acid, magnesium salt (PFOS-Mg) | 91036-71-4 |
| | (PFOS-Na) Perfluorooctanesulfonic acid, sodium salt (PFOS-Na) | 4021-47-0 |
| | Piperidine 1,1,2,2,3,3,4,4,5,5,6,6,7,7,8,8,8- heptadecafluorooctanesulfonate | 71463-74-6 |
| PFOA, & (PFOA, its salts & derivatives) | (Perfluorooctanoic acid) (PFOA) | 335-67-1 |
| | (PFOA-Na) Sodium perfluorooctanoate (PFOA-Na) | 335-95-5 |
| | (PFOA-K) Potassium perfluorooctanoate (PFOA-K) | 2395-00-8 |
| | (PFOA-Ag) Silver perfluorooctanoate (PFOA-Ag) | 335-93-3 |
| | (PFOA-F) Perfluorooctanoyl fluoride (PFOA-F) | 335-66-0 |
| | (APFO) Ammonium pentadecafluorooctanoate (APFO) | 3825-26-1 |
| | (PFOA-Li) Lithium perfluorooctanoate (PFOA-Li) | 17125-58-5 |
| | (PFOA-Co) Cobalt perfluorooctanoate (PFOA-Co) | 35965-01-6 |
| | (PFOA-Cs) Cesium perfluorooctanoate (PFOA-Cs) | 17125-60-9 |
| | (PFOA-Cr(3 ⁺)) Octanoic acid, 2,2,3,3,4,4,5,5,6,6,7,7,8,8,8- pentadecafluoro-, chromium(3+) (PFOA-Cr(3 ⁺)) | 68141-02-6 |



(No.): ETR24505668

(Date): 14-Jun-2024

(Page): 12 of 24

Test Report

(EVERLIGHT ELECTRONICS CO., LTD.)

6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

(Group Name)

423-52-9

PFOA, &

45285-51-6



(No.): ETR24505668

(Date): 14-Jun-2024

(Page): 13 of 24

Test Report

(EVERLIGHT ELECTRONICS CO., LTD.)

6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

/ Analytical flow chart of heavy metal

These samples were dissolved totally by pre-conditioning method according to below flow chart.


Cr⁶⁺ test method excluded

Test Report

(EVERLIGHT ELECTRONICS CO., LTD.)
 6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

/ Flow chart of stripping method for metal analysis


/ The plating layer
 of samples were dissolved totally by pre-conditioning method according to below flow chart.
 Cr⁶⁺ test method excluded



Test Report

(EVERLIGHT ELECTRONICS CO., LTD.)
6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

/ Analytical flow chart - PBBs/PBDEs




Test Report

(EVERLIGHT ELECTRONICS CO., LTD.)
6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

/ Analytical flow chart - Phthalate


/Test method: IEC 62321-8



Test Report

(EVERLIGHT ELECTRONICS CO., LTD.)
6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)


/ Analytical flow chart - HBCDD



Test Report

(EVERLIGHT ELECTRONICS CO., LTD.)
6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)


/ Analytical flow chart - Halogen



Test Report

(EVERLIGHT ELECTRONICS CO., LTD.)
6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)


(/ /) / Analytical flow
chart - PFAS (including PFOA/PFOS/its related compound, etc.)



Test Report

(EVERLIGHT ELECTRONICS CO., LTD.)
6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

Analytical flow chart - PAHs (Polycyclic Aromatic Hydrocarbons)




Test Report

(EVERLIGHT ELECTRONICS CO., LTD.)
 6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

() / Analytical flow chart of elements (Heavy metal included)

These samples were dissolved totally by pre-conditioning method according to below flow chart.

/Reference method US EPA 3051A US EPA 3052



* US EPA 3051A

/ US EPA 3051A method does not add HF.


Test Report

(EVERLIGHT ELECTRONICS CO., LTD.)
 6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

ICP-OES

(Flow chart of digestion for the elements analysis performed by ICP-OES)

/ These samples were dissolved totally by pre-conditioning method according to below flow chart.



| | |
|--------------------------------------|---|
| / Steel, copper, aluminum, solder | / Aqua regia, HNO ₃ , HCl, HF, H ₂ O ₂ |
| / Glass | / HNO ₃ , HF |
| / Gold, platinum, palladium, ceramic | / Aqua regia |
| / Silver | / HNO ₃ |
| / Plastic | / H ₂ SO ₄ , H ₂ O ₂ , HNO ₃ , HCl |
| / Others | / Added appropriate reagent to total digestion |

Test Report

(EVERLIGHT ELECTRONICS CO., LTD.)
6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

* / *

(The tested sample / part is marked by an arrow if it's shown on the photo.)

ETR24505668 NO.1



ETR24505668 NO.2



Test Report

(EVERLIGHT ELECTRONICS CO., LTD.)

6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)



** (End of Report) **

